

PROPERTY	UNIT	RESULT	TESTING METHOD
Cell structure	—	Closed very fine	—
Density (range)	kg/m ³	32 ~ 38 ± 10%	ASTM D-1622
Thermal conductivity	BTU in/ft ² .hr.°F W/mk	0.1789 0.0258	ASTM C-518
R-Value (Resistance to heat transfer)	hr. F. ²⁰ /BTU.in mk/W	5.590 0.968	ASTM C-518
Compressive strength	kPa	250 ~ 400	ASTM D-1621
Water Absorption by volume	%	≤ 0.3	ASTM C-272
Edge profile	—	Butt, Ship lap Tongue & groove	—

Platinum Member



PAKISTAN
GREEN BUILDING COUNCIL

ISO 8001-2015



www.jumbolon.com | jumbolon

UAN 0331 1111666

0322 9001 237 | 0333 4311 080

LAHORE 0322-9001237, 0322-9001244, KARACHI 0300-8260878, 0322-2006106, 0322-2006101, ISLAMABAD / RAWALPINDI 0322-9001273, 0322-9001274 PESHAWAR / MARDAN 0322-9001255, QUETTA 0333-4311080, 081-2836162, D.I. KHAN 0322-9001256, MULTAN 0322-9001260, SAHIWAL 0321-6952990, BAHAWALPUR 0322-9001265, RAHIM YAR KHAN 0322-9001263, SIALKOT 0322-9001284, SUKKUR 0322-9001260, LARKANA 0322-9001260, HYDERABAD 0322-2006112, FAISALABAD 0322-9001257, 0322-9001259, GUJRANWALA 0322-9001249, GUJRAT 0322-9001244

